

Technical Data Sheet

Performance	PVC Strip Curtain	Unit
Density	1.2	g/cm ³
Elongation at break	Length ways: ≥ 300	%
	Crosswise: ≥ 300	%
Hardness Shore A	75+-5	Shore A
Flexibility	-40 No Break	Degrees C
Water Absorption	0.1	%
Resistance of Continued rupture	>300	%
Reaction to Fire	Self-extinguishing	-
Flammability	Inflammable	-
Airborne Insulation	30dB	-
Light Transmission	≥ 70	%
Width warp	+2mm	mm
Length warp	+2mm	mm
Heat ageing loss (80°C+-2°C)	Length ways ≤ 2.0 Transverse ≤ 1.2	%